

TEROSON RB R2000 HS

July 2013

PRODUCT DESCRIPTION

TEROSON RB R2000 HS provides the following characteristics:

Technology	Highly Abrasion Resistant Coating Material for Underbody Coating, Road Stone Anti-Chip, Sound Damping
Base	Rubber / Resins

TEROSON RB R2000 HS is a solvent containing coating material, free of bitumen, based on rubber/resins. After complete drying, the coating exhibits a permanently elastic corrosion protection with good aging characteristics and no cracking at low temperatures, due to its combination of raw materials. The dry film adheres well to cleaned underbodies, also to painted surfaces and exhibits a very high abrasion-resistance.

Painting with standard automotive paints (conventional and water based) is possible under the following conditions:

- allow minimum 16 hours drying of the coating
- apply a fine paint mist prior to final painting
- final painting only after beginning of drying of the pre-painting subsequent oven drying at 60°C possible.

APPLICATION AREAS

TEROSON RB R2000 HS is suitable for repair work on the underbody, wheel house, front and rear aprons, spoilers, door sills, particularly as protection against road stones. The material is used as coating for painted parts or primer surfaced metals on the underbody and for repair works on coatings which are based on rubber/resins. TEROSON RB R2000 HS is also suitable for sound damping of wheel houses and side walls, and for covering and sealing of repair jobs, welding seams and overlaps.

TECHNICAL DATA

(Typical Test Results)

Colour	black , grey, white
Odour	of petroleum spirit
Consistency	thick liquid
Density	approx. 1.22 g/cm ³
Solids	approx. 64 %
Sag resistance	good

Layer thickness wet	1 mm
Skin formation time	2 to 4 hrs
Curing through	24 to 48 hrs
Abrasion resistance	very high
Application temperature	10 to 25 °C
In service temperature	-25 to 80 °C
short exposure (up to 1h)	100 °C

PRELIMINARY STATEMENT

Prior to application it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

Pretreatment

Surfaces to be treated with TEROSON RB R2000 HS have to be cleaned well and rust must be removed. The areas must be dry and free of grease, dirt and to a great extent free of dust. Areas not to be coated should be covered with masking paper. In the case of new vehicles, protective wax must be steam-cleaned. If applied to older vehicles, watch out for beginning of rust formation, which has to be removed with a wire brush.

Application

TEROSON RB R2000 HS is applied with the Teroson UBC-Gun from 1-l-cans; application pressure: 4 - 5 bar. Shake the can well up side down for 1 minute before use. Opened containers must not be left open because the material will form a skin. On vertical surfaces, the underbody coating can be applied in one step up to 1 mm layer thickness (wet film). In order to avoid bare patches, the material should be sprayed in criss-cross fashion. Under favourable weather conditions, the vehicle is ready for use 2 - 4 hours after application. For final drying 24 - 48 hours are necessary.

Important

Do not spray on joints, engine, drive, cardan shaft, exhaust, catalyst and brake system. After use blow through Teroson-UBC Pistol and then purge with Teroson FL.

**Clogging of the pistol may cause the tin to burst.
Read instruction leaflet of the pistol!**

TEROSON RB R2000 HS

July 2013

Finishing Treatment

Remove excess spray immediately with benzine or Teroson FL.

STORAGE

Frost sensitive	no
Recommended storage temperature	10 to 25 °C
Shelf life	18 months in original packaging

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including**

warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Henkel AG & Co. KGaA

D-40191 Düsseldorf. Germany
Phone: +49-211-797-0
www.henkel.com

Henkel Central Eastern Europe GmbH

A-1030 Wien. Austria
Phone: +43-1711-040
www.henkel.com

Henkel & Cie AG

CH-4133 Pratteln. Switzerland
Phone: +41-61-825-7000
www.henkel.com

